

HG108 Thetford

Brushed, Smoked and UV Colour Oiled Plank



Product Details

Product Code	HG108
Collection	Heritage
Construction	Engineered
Species	Oak
Product Type	Engineered Plank
Surface	Brushed, Smoked & Colour Oiled
Finish	UV Cured Oil
Dimensions	190 x 14/3 x 1900 mm
Top Layer	3 mm – Solid European Oak
Core Layer	11 mm – Multi Layer Eucalyptus & Poplar
Grade	Rustic
Pack Size	2.888 m ²
Pack Contents	6 Boards – May Include 2 split lengths
Joint Type	Tongue & Grooved
Edge Profile	Bevel Edged on 4 sides

Technical Information

Full documented evidence of legality of timber FSC® Certification FSC® 100% (TT-COC-004200) PEFC® Certification Not available with this product Janka Hardness Oak 1360 lbf (6000N) Slip Resistance EN 14231 (Test Result 58/44 PTV) European Reaction to Fire Classification Release of Formaldehyde EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK) Tog Rating 1.13	Toominoar imormatic	711
PEFC® Certification Not available with this product Janka Hardness Oak 1360 lbf (6000N) Slip Resistance EN 14231 (Test Result 58/44 PTV) European Reaction to Fire Classification Release of Formaldehyde EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	UKTR / UK Timber Regulation	0 ,
Janka Hardness Oak 1360 lbf (6000N) Slip Resistance European Reaction to Fire Classification Release of Formaldehyde EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	FSC® Certification	FSC®100% (TT-COC-004200)
Slip Resistance EN 14231 (Test Result 58/44 PTV) European Reaction to Fire Classification EN 13501-1 (test result Dfl-s1) Release of Formaldehyde EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	PEFC® Certification	Not available with this product
European Reaction to Fire Classification Release of Formaldehyde EN 13501-1 (test result Dfl-s1) EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	Janka Hardness	Oak 1360 lbf (6000N)
Classification EN 13501-1 (test result Dfl-s1) Release of Formaldehyde EN 717-1 (Test result E1) Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	Slip Resistance	EN 14231 (Test Result 58/44 PTV)
Thermal Conductivity EN 12524 (Test result: 0.16W/mK)	•	EN 13501-1 (test result Dfl-s1)
,	Release of Formaldehyde	EN 717-1 (Test result E1)
Tog Rating 1.13	Thermal Conductivity	EN 12524 (Test result: 0.16W/mK)
	Tog Rating	1.13

Grading: Rustic

Rustic Floors can contain varying size live and filled dead knots. Colour variation, sapwood, heartwood and end-checks (filled splits).

V4 Wood Flooring is chosen for its natural beauty, therefore grading criteria is always an approximation as every piece of timber is different. If further selection is needed please allow for extra material upon installation.

Installation Methods

All V4 floors should be installed by experienced flooring installers who have read and understood the appropriate installation guides at www.v4woodflooring.co.uk

Fully Bonded	Yes*
Secret Nailed	No
Floated on Underlay	Yes*
Over Underfloor Heating	Yes* (fully bonded installation recommended)

Maintenance Schedule Advice

Avoid scratches by minimising grit and dust, install doorway entrance mats and felt pads to protect furniture. Use PH neutral cleaners and avoid soaking the floor with water. For more detailed advice visit www.v4woodflooring.co.uk



The mark of responsible forestr

V4 Wood Flooring®

*Subject to correctly prepared and compatible subfloor and in conjunction with correct installation